## NEKOOSA4 mil Matte White Translucent, RemovableTECHNICAL DATAAdhesive, 90# Layflat liner

|             | Γ                         | SPMTUR               |
|-------------|---------------------------|----------------------|
|             |                           |                      |
| Finish      |                           | Matte                |
| Color       |                           | White                |
| Adhesive    |                           | Removable - R32      |
| Film        |                           | Polymeric Flex Vinyl |
| Liner       |                           | 90# Layflat liner    |
| Opacity     |                           | 75% typical          |
| Gloss Level |                           | 5-10 % typical       |
| Thickness   | Film                      | 3.2 ± 0.2 mil        |
|             | Film With Adhesive        | 4.2 ± 0.3 mil        |
|             | Total Thickness           | 10.7 ± 0.4 mil       |
| Adhesion    | SS 15 min room temp dwell | 5 - 10 oz/in         |
|             | SS 24-Hr room temp dwell  | 10 - 15 oz/in        |
| Weight      | Film With Adhesive        | 110-120 gsm          |
|             | Total With Liner          | 260-275 gsm          |

## **Conditions for Use**

**Physical Proper** 

| Shelf Life           | 1 year*                    |
|----------------------|----------------------------|
| Durability Outdoor   | Up to 5 years**            |
| Indoor               | Up to 7 years              |
| Min Application Temp | 40°F (4°C)                 |
| Service Temp Range   | -10 to 140°F (-23 to 60°C) |
| Solvent Resistance   | Good**                     |
| Water Resistance     | Good                       |

 $^{st}$  When stored at 70  $^{\circ}$ F and 50% relative humdity

\*\* Edge sealer recommended for outdoor and high solvent exposure areas

## Disclaimer

The information provided herein is correct to the best of Nekoosa's knowledge, however, should not be construed as specifications. No liability for any errors, facts or opinions are accepted. Customers must satisfy themselves as to the suitability of this product for their application. No responsibility for any loss as a result of any person placing reliance on any material contained herein will be accepted.