

CHALKTALK®

CHALKBOARD
FILM



Printable, chalkboard film with removable adhesive for all your creative uses.

ChalkTalk

5 mil textured matte black vinyl facestock, high-peel removable adhesive, 90# layflat polycoated paper liner

High-peel adhesive properties allow for a broader range of applications surfaces like painted plywood, textured walls and low-to-no VOC paints

Suitable for indoor and outdoor applications (<6 months clean removability from application surface)

Write with chalk or liquid chalk ink pens for best results*

Wipes clean with a damp cloth

Print Compatibility: Wide Format (Solvent, Eco-Solvent, Latex and UV) and Screen

Easy to apply and remove from these surfaces:

WOOD PANELING	POLISHED STONE	STAINLESS STEEL	SMOOTH PAINTED WALLS
TEXTURED PAINTED WALLS	LOW VOC PAINT	CONCRETE	PAINTED PLYWOOD

*For best results, write on ChalkTalk with chalk ink pens.

Applications

- Restaurant Menu Boards
- Retail Promotional Displays
- Point-of-Purchase Wall Signage
- To-Do List
- Textured Wall Graphics
- Seasonal Promotional Signage
- Trade Show & Event Signage
- Large Format Graphics
- Grocery Store Displays




CHALKTALK® CHALKBOARD FILM



STOCKED PRODUCTS ▶

	Finish/Color	SKU #	Size	Film Thickness	Adhesive	Liner	Rolls/Carton
Wide Format	Textured Matte Black	SPMCHK2475	24" x 75 ft	5 mil	High Peel Removable	90# Layflat	1
	Textured Matte Black	SPMCHK5475	54" x 75 ft	5 mil	High Peel Removable	90# Layflat	1

CHALKTALK® CHALKBOARD FILM



CUSTOM SIZE OFFERING ▶

	Finish/Color	SKU #	Size	Film Thickness	Adhesive	Liner	Wgt/MSI
Non Top Coated - Screen							
	Textured Matte Black	SPMCHK	54"	5 mil	High Peel Removable	90# Layflat	.62#

Custom Size Offering: Custom converted sheet and roll options available to meet your specific requirements.

TECHNICAL DATA ▶

Physical Properties			ChalkTalk		
		Test Method			
Thickness	Film	TAPPI T-411	5.0 +/- 0.3 mils (127 +/- 8 µm)		
	Film w/ Adhesive	TAPPI T-411	6.0 +/- 0.2 mils (152 +/- 5 µm)		
	Total Thickness	TAPPI T-411	5.0 +/- 0.3 mils (127 +/- 8 µm)		
Weight	Film w/ Adhesive	TAPPI T-410	190-195 gsm		
	Total w/ Liner	TAPPI T-410	340-350 gsm		
Opacity		ASTM D1003	100%		
Gloss Level		ASTM D523	1.5%		
Surface Energy		ASTM D2578	33 min dyne/cm		
Dimensional Stability		ASTM D1204	1% - 5%		
Tensile Strength	MD	ASTM D882B	4500 +/- 450 psi		
	TD	ASTMD1204	3500 +/- 350 psi		
Elongation	MD	ASTM D88SB	130% - 180%		
	TD	ASTM D882B	130% - 180%		
Adhesion 180°	Surfaces	Test Method	1 min	15 min	24 hours
	Stainless Steel	ASTMD3330	25 oz/in	45 oz/in	45 oz/in
	Acrylic		35 oz/in	40 oz/in	55 oz/in
	Aluminum		15 oz/in	40 oz/in	40 oz/in
	Ceramic		30 oz/in	33 oz/in	50 oz/in
	Polycarbonate		45 oz/in	55 oz/in	65 oz/in
	Polypropylene		5 oz/in	10 oz/in	10 oz/in
	Wood (Sealed)		1.5 oz/in	1.7 oz/in	2 oz/in
Fire Rating				ASTM E84 Class 1 or A	

Conditions for Use	
Shelf Life	1 year
Outdoor Durability*	6 months
Indoor Durability	1 year
Min Application Temp	40° F (4.4° C)
Service Temp Range	-10° to 140° F (-23° to 60° C)
Solvent Resistance	Good
Water Resistance	Excellent

*For clean removability

The information provided herein is correct to the best of Nekoosa's knowledge, however, should not be construed as specifications. No liability for any errors, facts or opinions are accepted. Customers must satisfy themselves as to the suitability of this product for their application. No responsibility for any loss as a result of any person placing reliance on any material contained herein will be accepted.